




01201522

Type	PD200
Film usage	Greenhouse cover
Width	Up to 16 meters
Thickness	200 micron
Length	As required



Specification	Test Method	Units	Value
Light Transmission	GB/T 2410-2008	%	90
Light Diffusion	GB/T 2410-2008	%	65
Tensile Strength at break [MD/TD]	GB/T 1040.3-2006	Mpa	30
Elongation at break [MD/TD]	GB/T 1040.3-2006	%	750
Tear Resistance [MD/TD]	QB/T 1130-1991	gr./mm	10000
Falling Dart Impact	GB/T 9639.1-2008	gr.	1000
Anti-Drip	—		YES
Anti-Sulfur	—	PPM	500
Warranty	—	—	5 Years Under Proper condition

LIDOU TECH